

AMENDMENTS TO THE SPECIFICATION

Please replace the paragraph at page 94, lines 27-28, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid

Please replace the paragraph starting at 98, lines 15-16, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph at page 103, lines 13-14, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid

Please replace the paragraph at page 110, lines 8-9, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph at page 114, lines 11-12, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph at page 119, lines 20-21, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph at page 126, lines 22-23, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl-phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph at page 131, lines 26-27, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl phenoxyacetate~~ nonylphenoxy acetic acid (NPA)

Please replace the paragraph starting at page 139, lines 3-4, with the following paragraph.

Component (C-2)

C-2-1: ~~nonyl phenoxyacetate~~ nonylphenoxy acetic acid

Please replace the paragraph at page 145, lines 11-12, with the following paragraph.

C-2) compounds represented by the formula (14)

C-2-1: ~~nonyl phenoxyacetate~~ nonylphenoxy acetic acid

Please replace the paragraph at page 151, lines 21-22, with the following paragraph.

(C-2) compounds represented by the formula (20)

C-2-1: ~~nonyl phenoxyacetate~~ nonylphenoxy acetic acid

Please replace Table 1 on page 147 with the following:

Table 1

Example		1	2	3	4	5
Base oil 1		98.90	-	-	-	-
2		-	98.70	98.50	98.55	98.45
A-2-1		0.30	0.20	0.30	-	-
A-2-2		-	-	-	0.30	0.30
B1		0.30	0.30	-	-	-
B2		-	-	0.30	0.30	0.30
C-1-1		-	-	-	0.05	0.05
C-2-1		-	-	0.10	-	0.10
<del>C-A-1</del> <u>G-A-1</u>		0.50	0.50	0.50	0.50	0.50
<del>C-B-1</del> <u>G-B-1</u>		-	0.30	0.30	0.30	0.30
Amount of sludge (mg/45g) in the thermal stability test	10 days	1.8	1.3	2.8	1.3	3.5
	20 days	7.2	8.5	7.8	5.3	8.3
SRV (frictional index)		0.118	0.119	0.118	0.113	0.110
Antiemusifying property		40-40-0 (5)	40-40-0 (10)	40-40-0 (10)	40-40-0 (10)	40-40-0 (10)
<u>Abrasion resistance</u> <u>(abrasion amount</u> <u>[mg])</u>		10.5	11.3	12.4	10.8	9.8

Please replace Table 2 on page 148 with the following:

Table 2

		Test Example 1	Test Example 2	Test Example 3	Test Example 4
Base oil 1		98.90	-	-	-
2		-	98.10	98.60	98.60
A-2-1		0.30	-	-	-
A-2-2		-	0.30	0.30	0.30
B1		-	0.30	-	-
<del>C-A-1</del> <u>G-A-1</u>		0.50	0.50	0.50	0.50
<del>C-B-1</del> <u>G-B-1</u>		0.30	0.30	0.30	0.30
E1		-	0.50	-	-
H1		-	-	-	0.30
K1		-	-	0.30	-
K2		-	-	-	-
Amount of sludge (mg/45g) in the thermal stability test	10 days	10.3	11.8	7.7	11.6
	20 days	28.7	35.2	12.4	27.9
SRV (frictional index)		0.120	0.132	0.122	0.120
Antiemulsifying property		40-40-0 (5)	40-40-0 (20)	15-20-45 (80)	20-26-34 (80)
<u>Abrasion resistance</u> ( <u>abrasion amount</u> <u>[mg]</u> )		9.5	14.3	15.8	10.2

Please replace Table 3 on page 149 with the following:

Table 3

		Test Example 5	Test Example 6	Test Example 7	Test Example 8
Base oil 1		-	-	-	-
2		98.60	98.30	98.60	98.30
A-2-1		-	-	-	-
A-2-2		0.30	0.30	0.30	0.30
B1		-	-	-	-
<del>C-A-1</del> G-A-1		0.50	0.50	0.50	0.50
<del>C-B-1</del> G-B-1		0.30	0.30	0.30	0.30
E1		-	-	-	-
H1		-	0.30	-	0.30
K1		0.30	0.30	-	-
K2		-	-	0.30	0.30
Amount of sludge (mg/45g) in the thermal stability test	10 days	5.8	1.3	13.5	14.3
	20 days	11.2	12.7	32.4	33.8
SRV (frictional index)		0.123	0.122	0.124	0.124
Antiemusifying property		20-28-34 (60)	19-28-33 (60)	24-23-53 (60)	22-18-38 (80)
Abrasion resistance (abrasion amount [mg])		13.5	12.7	15.7	14.3